

Magicote 1 Part System

Swimming Pool Scratch Coat

Limitations: All materials and surfaces to be coated should remain between 40° F and 120° F for 24 hours prior and 24 after installation. Do not apply in rain or extremely high humidity. Protect "Liquid Resin" from freezing. Plaster should be applied to Magicote within 7 days or you must reapply Magicote. **DO NOT USE OVER PAINTED OR PLASTIC FINISHES.**

Packaging: Magicote is formulated in units consisting of one 50 pound bag of a Magicote powder. This is mixed at the job-site as per mixing instructions.

Surface Preparation: Check completely for hollow areas and remove all loose plaster. Remove all mildew, algae, fungus and rust by either sand blasting, pressure washing or with an acid wash that must be followed by neutralization with soda ash. If surface is painted, peeling or flaking, the surface must be sand or water blasted. Regardless of method used, thoroughly wash down and let pool drain until there is no standing water present. **NOTE:** Special attention is required on pools below water table and/or pools with leaks.

Mixing: Pour 2 gallons of water into a clean mixing container with a flat bottom. Add Magicote powder while continuously mixing with a mechanical mixer to desired consistency. Continue mixing for 2- 4 minutes until Magicote is completely dispersed. **NEVER MIX LESS THAN 1 GALLON OF WATER [32 oz.] OR MORE THAN 2 GALLONS OF WATER [96 oz.]**

Water Chemistry: The pool water must be carefully balanced from the initial fill and constantly maintained within recommended NSPI guidelines. Maintaining proper chemical balance from first fill is essential to maximize the life of the pool surface. Please follow manufacture's directions concerning start-up techniques and maintenance programs.



Application: Let material set for 1 minute then, using a clean textured roller and/or a broom or brush, rough up the surface to the desired finish. Material thickness can be adjusted by adding a small amount of "Cement Mix" if too thin or water if too thick. Adjust only 1 time. **DO NOT RETEMPER MIX.** Once Magicote is mixed to correct consistency, apply immediately. Do not let the material stand unused. Apply mixed Magicote with 1¼ nap roller to steps at shallow end of pool and let material set for approximately 1- minute, then rough up surface to desired finish with clean textured roller. Continue this same process to the floor surface last. Starting at the deep end of pool, make sure application is uniform in thickness and texture.

Curing: Minimum cure is achieved in 5- hours. Setting and drying time may vary according to atmospheric conditions. For best results, wait 12 hours before plastering.

Plastering: Lightly mist Magicote with clean cool water prior to plastering to permit proper hydration. Make sure Magicote is free of any foreign matter before plastering. Leave no standing water.

Coverage: One 50 lb. bag covers 175- 200 square feet of surface area.

Clean up & Storage: Clean hands, tools and containers with warm soapy water. Caution: After handling, wash hands thoroughly before eating or smoking. Do not take internally. **KEEP OUT OF REACH OF CHILDREN.**

Limited Warranty: Magic Marcite, Inc. will replace any material proved defective with the maximum shelf life on unused material of up to one (1) year. If our products are not found to conform to our high standards, notify Magic Marcite, Inc. immediately in writing. There is no other obligation expressed or implied. We assume no liabilities for damages or any kind of suitability of the product. An intended use shall be solely up to the user.

WARNINGS: Eye and skin irritant. Avoid contact with eyes. Do not take internally.

First Aid: In case of contact with eyes, flush with large amounts of water for at least 15 minutes. For skin, wash affected area with soap and water. If irritation persists, see a physician. If ingested, contact a physician immediately.

KEEP OUT OF THE REACH OF CHILDREN

PROTECT FROM FREEZING